

N28

LEAD SILICONE SEALANT

Demsun N28 is a one component, high quality Neutral curing 100% silicone sealant designed for applications where **long term durable plumbing, spouting, roofing, flashing, cladding and guttering are required**. It is suitable for sealing of connection joints between a variety of substrates.

FEATURES & BENEFITS

- Outstanding adhesion without primer on joining elements made from brick, stone, concrete, wooden, plastic, steel, aluminum, zinc, porcelain, ceramic, PVC, metal, glass and porous surfaces,
- Highly elastic, +/-25% movement capability
- UV, water and weather proof
- Non-corrosive neutral cure
- Fast curing
- Low odor
- Interior/exterior use
- Easy to apply
- Chemically resistant
- Non-sag

APPLICATION AREAS

- Joints and cracks in gutters
- Flashing
- Downpipes
- Lap joints
- Skylights
- Cladding walls
- Vent and HVAC ducts systems

INSTRUCTIONS

- Ensure that surfaces to be sealed are clean, dry and grease free.
- The application temperature must be between +5°C and +40°C.

TECHNICAL DATA SHEET (TDS)

- In order to reduce the deformations of the joints, their depth must be much less than their width, minimum dimensions are 5x5 mm, for wider joints the depth should be preferably half of the width and it is adjusted by the use of a backup material.
- After the application, the sealant must be tooled with light pressure within 5 minutes to spread the material against the joint surfaces and to obtain a professional finish.
- Excess uncured sealant may be cleaned with solvent. Cured sealant can be removed barely mechanically.

- Recommended joint widths are >10 mm and < 35 mm.
- Joint width and depth ratio should be about 2:1.

Consumption (approx.)

Joint Width	10mm	15mm	20 mm
Joint Depth	6mm	8mm	10 mm
Efficiency /310 ml	5 meters	2.5 meters	1.5 meters

Surface Preparation

Following cleaning procedure and materials are recommended:

Glass	Degrease with alcohol or MEK
Aluminium, light alloys and stainless steel	Degrease with alcohol or MEK
Other Metals	Lightly abrade then degrease as above
Wood	Lightly abrade surface then remove dust
Plastics	Degrease using an agent recommended by plastics manufacturer
Concrete and other alkaline Surfaces	Brush and remove dust

STANDARDS

Meets or exceeds the requirements of the following specifications:

- The French VOC requirements for class A+
- ISO 11600 F & G 20LM.
- CE marked for EN 15651 for façade, glazing and sanitary applications.
- The requirements of VOC content specifications in LEED credit EQc4.1 “Low-emitting products” of SCAQMD rule 1168.

RESTRICTIONS;

- It must not be used in totally confined spaces where sealant cannot cure due to lack of atmospheric moisture.
- Not over paintable.
- Do not use in conjunction with bitumen asphalt, neoprene and certain organic elastomers.
- It is not suitable for food contact applications.
- Can yellow if exposed to bleach or HCL based brick cleaners whilst curing.

TECHNICAL DATA SHEET (TDS)

STORAGE AND SHELF LIFE;

The shelf life is 12 months if stored in unopened-original package in a dry place at temperatures between +5°C and +25°C.

SAFETY & DISPOSAL

Inhalation of the sealant vapor for a long period must be avoided. The application area must be ventilated properly. The uncured sealant must not be contacted for a long period. Cured silicone rubber bears no risk to health. temperatures between +5°C and +25°C. Check MSDS guidelines for disposal and further information concerning safety.

PROPERTIES

Basis	: Silicone Polymer(Oxime)	
Curing System	: Neutral	
Density (Transparent and Aluminum)	: 0,98± 0.03 g/ml	(ASTM D 792)
Density (Other Colors)	: 1,30± 0.03 g/ml	(ASTM D 792)
Hardness Shore A (Transparent and Aluminum)	: 25-30 (after 28 days)	
Hardness Shore A (Other Colors)	: 30-35 (after 28 days)	
Tensile Strength	: ≤ 0,4 N/mm ² (23°C and 50% R.H)	(ISO 8339)
Skin formation	: 5-10 min. (23°C and 50% R.H)	
Curing Rate	: Min. 3 mm/day (23°C and 50% R.H)	
Elongation At Break (Transparent and Aluminum)	: ≥ 300%	(ASTM D412)
Elongation At Break (Other Colors)	: ≥ 250%	
Elastic Recovery	: Approx. 100%	(ISO 7389)
Sagging	: 0 mm	(ISO 7390)
Temperature Resistance	: -60°C to +180°C	
Application Temperature	: +5°C to +40°C	

PRODUCT

Product Type	Volume	Package
Grey	310ml	24

DISCLAIMER

TECHNICAL DATA SHEET (TDS)

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.