

PRODUCT DATA

2990 STAINBLOCKER

DESCRIPTION

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker is a matt white high-pigmented coating based on a plasticized acrylic resin for the permanent isolation of problem stains from nicotine, soot, tar and rust and the effects of moisture, graffiti and a numerous other colourings.

RECOMMENDED USES

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker is a renovation paint which can be applied directly on ceilings, plaster, cement, wood, concrete, wallpaper, isolation walls, old paints, etc.

RUST-OLEUM® HARD HAT Aerosol 2990 Stainblocker can be used as topcoat or can be recoated with standard wall paints.

TECHNICAL DATA

Appearance: Matt
Colour: White
Propellant: Propane/Butane
VOC-content: 538 g/l

Drying times 20°C/50% r.h.
Tack free: 5 minutes
To recoat: Wet in wet / after ½ hour
Full hardness 24 hours

COVERAGE

Theoretical: 2,1 m² per aerosol at 30 µm dry
Practical coverage depends on many factors such as roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove dirt, grease, oil, loose rust and all other surface contaminants by appropriate means. Sand intact coatings to roughen the surface slightly. The surface must be clean and dry during application.

DIRECTION FOR USE

Remove cover cap. Shake vigorously for at least one minute after the rattle of mixing ball is heard. Shake frequently during use. Hold can approx. 25 cm from surface. Use back and forth motion keeping can parallel with surface. Ensure that can is in motion when spray button is pressed to avoid runs and sags. Apply several thin layers at a few minutes interval to achieve adequate coating thickness.

After use turn can upside down and press spray button for 2 - 3 seconds to clean valve.

APPLICATION CONDITIONS

For optimum results the relative humidity should be below 85% and the temperature of the can above 0°C.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE CONDITIONS

3 years from date of production, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35° C.