



# AURELIA® ABSOLUTE 100

3.2mil, Nitrile Powder Free Examination Gloves

**AURELIA® GLOVES**  
A SUPERMAX HEALTHCARE BRAND

<b>Regulations</b>	PPE Regulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
<b>Quality Standards</b>	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
<b>Harmonised Standards</b>	BS EN ISO 374 - 1,2,4,5 Protective gloves against dangerous chemicals and microorganisms. BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1184: 2002. Materials and articles in contact with foodstuffs.



10 x 100

XS	S	M	L	XL
9899A5	9899A6	9899A7	9899A8	9899A9

Sizes & Dimensions	Single wall thickness	Physical Properties													
<p>XS 70+10 mm S 80+10 mm M 95+10 mm L 110+10 mm XL &gt; 110 mm</p>	<p>min. 240 mm min. 240 mm min. 240 mm min. 240 mm min. 240 mm</p> <p>① min. 0.10 mm ② min. 0.06 mm ③ min. 0.05 mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N	
	Unaged	Aged													
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa													
Elongation	Min. 500%	Min. 400%													
Strength at Break	Min. 6N	Min. 6N													



Nitrile



Powder Free



5 Years



Finger Textured



3.6g +/- 0.2g



Black

