



AURELIA® BOLD MAX

6mil, Nitrile Powder Free Examination Gloves

AURELIA® GLOVES
A SUPERMAX HEALTHCARE BRAND

Regulations	PPE Regulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
Harmonised Standards	BS EN ISO 374 - 1,2,4,5 Protective gloves against dangerous chemicals and microorganisms. BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1184: 2002. Materials and articles in contact with foodstuffs.



10 x 50

M L XL XXL
 9789A7 9789A8 9789A9 9789A0

Sizes & Dimensions		Single wall thickness	Physical Properties													
<p>M 95+10 mm L 110+10 mm XL 120+10 mm XXL > 120 mm</p>	<p>min. 240 mm min. 240 mm min. 240 mm min. 240 mm</p>	<p>① min. 0.20 mm ② min. 0.16 mm ③ min. 0.08 mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N	
	Unaged	Aged														
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa														
Elongation	Min. 500%	Min. 400%														
Strength at Break	Min. 6N	Min. 6N														



Nitrile



Powder Free



5 Years



Diamond



7.5g +/- 0.2g



Black

