



AURELIA® TRANSFORM 100

AURELIA® GLOVES
A SUPERMAX HEALTHCARE BRAND

3.2mil, Nitrile Powder Free Examination Gloves

Regulations	PPE Reugulation (EU) 2016/425 Medical Device Regulation (EU) 2017/745, 93/42/EEC
Quality Standards	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
Harmonised Standards	BS EN ISO 374 - 1,2,4,5 Protective gloves against dangerous chemicals and microorganisms. BS EN 455 1-4 Medical gloves for single use. EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1184: 1997. Materials and articles in contact with foodstuffs.

 10 x 100













XS
S
M
L
XL

9889A5 9889A6 9889A7 9889A8 9889A9

Sizes & Dimensions		Single wall thickness	Physical Properties													
 XS 70+10 mm S 80+10 mm M 95+10 mm L 110+10 mm XL > 110 mm	 min. 240 mm min. 240 mm min. 240 mm min. 240 mm min. 240 mm	 ① min. 0.10 mm ② min. 0.06 mm ③ min. 0.05 mm	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 14.0 MPa</td> <td>Min. 14.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 500%</td> <td>Min. 400%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 6N</td> <td>Min. 6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa	Elongation	Min. 500%	Min. 400%	Strength at Break	Min. 6N	Min. 6N	
	Unaged	Aged														
Tensile Strength	Min. 14.0 MPa	Min. 14.0 MPa														
Elongation	Min. 500%	Min. 400%														
Strength at Break	Min. 6N	Min. 6N														



Nitrile



Powder Free



5 Years



Micro



3.6g +/- 0.2g



Ice Blue

