

H3402 Coarse Safety-Grip™ Data Sheet

Subject	Result	Test method
Back carrier	0.1mm PVC	Calliper method
Total Applied Thickness	1.02mm	Calliper method
Type of adhesive	Solvent acrylic	N/A
Mineral type	Aluminium Oxide	N/A
Adhesion to steel (g/25.4mm ²)	1500 ↑	PSTC-4
Tensile strength (kg/25.4mm ²)	6.0 ↑	PSTC-31
Tear resistance (g)	5600 +/- 200	PSTC-39
Elongation at break	25% ↑	PSTC-31
Temperature range	-40°C to +80°C	See notes below
Maximum size of production roll	1168mmx100m	N/A
Resistance to water (months)	10	PSTC-35
Resistance to chemicals (months)	8	PSTC-35
Resistance to motor oil	Excellent	PSTC-35
Life (months)	12 to 24	PSTC-9

The above tests were performed by Adhesive Technical Services Ltd, original test data available on request.

Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
EN16165:2021 Pendulum Test Value (PTV)	0.99	0.80
DIN51130	R13	

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request.

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H3402N (Black)	9004	Black U	0	0
H3402Y (Yellow)	1023	113U	38.25	3
H3402V (Green)	6010	342U	1.5	5
H3402W(White)	9003	White	57.44	2.51
H3402 (Transparent)				
H3402D (Yellow/Black)				

Temperature Range

	Temperature	Observations
Black CoarseAnti-slip Tape H3402N	-40°C	No visible evidence of peeling or loss of adhesion
Black CoarseAnti-slip Tape H3402N	+80°C	No visible evidence of peeling or loss of adhesion

Alltheabovedataisforreferenceonly.

©Heskins Ltd 1997-2024

