GROUND

S \triangleright Ś

PROTECTION

Pro Titan Tank



Description

Pro Titan Tank is a multi-layer polyethylene membrane with an adhesive coating for post applied vertical applications as a waterproof membrane specifically designed and manufactured to perform as a methane, carbon dioxide, radon, VOC, hydrocarbon and other ground gas protection system.

Pro Titan Tank is a post applied waterproof and ground gas membrane offering a safe solution for the protection of buildings, structures and occupiers.

Pro Titan Tank complies with the latest codes of practice as published by BRE,CIRIA(748) and BSI (BS8485:2015+A1:2019 and BS 8102:2022). Suitable for use as ground gas/hydrocarbon protection for NHBC Green, Amber1, Amber2 and Red Site Characterisations.

Features

- · Exceptional chemical resistance
- Tough, durable design
- · Conforms with latest codes of practice as published by BRE, CIRIA and BSI
- · High resistance to ground gases
- Waterproof
- · Can be a fully welded system
- · Suitable for new build and refurbishment projects

Specification

- · BS 8485:2015+A1:2019 Code of practice for the design of protective measures for methane and carbon dioxide ground gases for new buildings
- · NBS Specification J40 Flexible waterproofing/damp proofing membrane including gas/hydrocarbon protection
- · NBS Specification J40/145 Loose laid weldable polyethylene gas retardant damp proofing
- · NBS Specification D21/350 Gas retardant membrane

Product Details

DMS 438

Storage

- Rolls of Pro Titan VOC should be stored on stable/level ground and stacked not more than five rolls high, with no other material stacked on top. The rolls can be stored outdoors when packaged, but should be protected from exposure to UV.
- Always store and transport in a secure position.

Packaging/Handling

· Roll weights can be more than 20kg and appropriate care and equipment is required for unloading and handling.

Associated Products

- Detailing Strip
- · Pro Titan Tape
- · Pro Titan External Tape

Technical Drawings

www.deltamembranes.com/technical-categories/technical-drawings





PRODUCT DATA SHEET

Pro Titan Tank

Technical Data

Physical Properties		
Characteristics	Test Method	Pro Titan Tank
Thickness	EN 1849-2	1.2mm
Width	EN 1849-2	0.9 or 0.3m
Length	EN 1849-2	20m
Weight	EN 1849-2	1350g/m ²

Hydraulic Press		
Characteristics	Test Method	Pro Titan Tank
Water Vapour Transmission Rate	EN 1931	0.11-0.18g/m²/day
Water Tightness (60 kPa)	EN 1928	PASS
Water Tightness (196 kPa - 20 m Water Head (Basement Application)	EN 1928	PASS

Mechanical Properties		
Characteristics	Test Method	Pro Titan Tank
Resistance to Static Load	EN 12730-B	>20kg
Puncture Resistance	EN 12236	>2.0kN
Tensile Strength (MD)	EN 12311-1	>550N/50mm
Tensile Strength (CMD)	EN 12311-1	>400N/50mm
Tensile Elongation (MD/(CMD)	EN 12310-1	>550%
Tear Resistance (MD/CMD)	EN 12310-1	>300N
Resistance to Impact	EN 12691-B	650mm
Reaction to Fire	EN 13501-1	E Class
Resistance to Artificial Ageing	EN 1296/EN 1928	PASS
Resistance to Chemicals	EN 1296/EN 1928	PASS

Compliance and Certification

Characteristics

CE Mark - EN 13967:2012

NHBC Standards Compliant

BS 8485:2015+A1:2019 Compliant (Methane and Carbon Dioxide Barrier)

CIRIA C748 Compliant (VOC Barrier)

BS 8102:2022 Compliant (Type A Waterproofing)

Vapour Permeability 100% Concentration		
Characteristics	Test Method	Pro Titan Tank
Transmission Rate of Benzene	EN ISO 15105-2	<3.6mg/m²/day
Transmission Rate of Toluene	EN ISO 15105-2	<13.8mg/m²/day
Transmission Rate of Ethyl Benzene	EN ISO 15105-2	<2.7mg/m²/day
Transmission Rate of Xylenes (M,P,O)	EN ISO 15105-2	<7.7mg/m²/day
Transmission Rate of Hexane	EN ISO 15105-2	<0.6mg/m²/day
Transmission Rate of Vinyl Chloride	EN ISO 15105-2	<0.05mg/m²/day
Transmission Rate of Trichloroethene (TCE)	EN ISO 15105-2	<54.7mg/m²/day
Transmission Rate of Tetrachloroethene (PCE)	EN ISO 15105-2	<26.2mg/m²/day
Transmission Rate of Naphthalene	EN ISO 15105-2	<0.0006mg/m²/day
Transmission Rate of CIS-1,2-Dichloroethylene	EN ISO 15105-2	<1.1mg/m²/day



PRODUCT DATA SHEET

Pro Titan Tank

Gas Permeability		
Characteristics	Test Method	Pro Titan Tank
Methane Permeability	EN ISO 15105-1	0.13ml/m²/day/atm
Methane Permeability (Jointed)	EN ISO 15105-1	1.00ml/m²/day/atm
Carbon Dioxide Permeability	EN ISO 15105-1	3.01ml/m²/day/atm
Vinyl Chloride Gas Permeability	EN ISO 15105-1	0.04ml/m²/day/atm
Radon Permeability	K124/02/195	1.0x10 ⁻¹² m ² /S

Durability and Chemical Resistance		
Characteristics	Test Method	Pro Titan Tank
Chemical Resistance - Sulphuric ACID (10% Solution of Sulphuric Acid (H ₂ SO ₄)) 50° For 56 Days	EN 14414-A	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Chemical Resistance - BASIC (Calcium Hydroxide Saturated Suspension) 50° For 56 Days	EN 14414-B	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Chemical Resistance - SOLVENTS (35% Diesel, 35% Paraffin, 30% Oil Hd30 (Vol.)) 50° For 56 Days	EN 14414-C	TENSILE STRENGTH RETAINED >80% RESULT - PASS
Chemical Resistance - SYNTHETIC LEACHATE (Mixture of 14 Acids, Chlorides, Sulphates & Phosphates) 50° For 56 Days	EN 14414-D	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Resistance to Leaching - HOT WATER (Deionised Water) 50° For 56 Days	EN 14415-A	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Resistance to Leaching - AQUEOUS ALKALINE (Saturated Calcium Hydroxide) 50° For 56 Days	EN 14415-B	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Resistance to Leaching - ORGANIC ALCOHOL (30% Methanol, 30% Isopropanol, 40% Glycol) 50° For 56 Days	EN 14415-C	TENSILE STRENGTH RETAINED 100% RESULT - PASS
Chemical Resistance - BENZENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 95% (MD), 102% (CMD) RESULT - PASS
Chemical Resistance - TOLUENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 94% (MD), 91% (CMD) RESULT - PASS
Chemical Resistance - ETHYL BENZENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 99% (MD), 97% (CMD) RESULT - PASS
Chemical Resistance - XYLENES - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 91% (MD), 106% (CMD) RESULT - PASS
Chemical Resistance - TCE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 99% (MD), 93% (CMD) RESULT - PASS
Chemical Resistance - PCE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 93% (MD), 93% (CMD) RESULT - PASS
Chemical Resistance - NAPTHALENE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 101% (MD), 93% (CMD) RESULT - PASS
Chemical Resistance - HEXANE - 100% Saturated Concentration	EN 14414-D (MOD)	TENSILE STRENGTH RETAINED 99% (MD), 104% (CMD) RESULT - PASS

Installation

It is essential that ground gas protection systems are installed correctly, meeting all applicable building standards and regulations. Installation of ground gas protection systems should be carried out by technicians who hold a valid NVQ Qualification in ground gas installation. All ground gas protection systems should be verified by an independent verification company and not the membrane manufacturer, installer or client. All joints should be heat welded where practical and possible.

Other Information

All data and information contained in these Product/Technical Data Sheets is up-to-date and correct as at the date of issue. The information given is suggested as guidance and should only be used for evaluating your specific application. Delta Membrane Systems Limited cannot control or anticipate the conditions under which this product may be used, each user should review the information in specific context of the planned use. The information contained in these Product/Technical Data Sheets should not be considered a warranty, expressed, or implied, including but not limited to a warranty of merchantability or fitness for a particular purpose. In no event shall Delta Membrane Systems Limited be liable for any incidental or consequential damages resulting from the use, misuse, or inability to use the product. This exclusion applies regardless of whether such damages are

